

BÜFA®-Bonding Paste 0072

UP Sandwich Adhesive

Prod. No. 7400072

Product description BÜFA®-Bonding Paste 0072 is a preaccelerated, highly reactive bonding paste/ sandwich adhesive with low density that is filled with organic light-weight fillers. It is based on a flexibilised mixture of unsaturated orthophthalic acid polyester resins dissolved in styrene. Because of its creamy consistency, it can be applied to the surfaces that are to be bonded very easily and quickly.

Applications BÜFA®-Bonding Paste 0072 is a so-called sandwich adhesive that was especially developed for bonding GRP laminates with core layers made of synthetic rigid foam or balsa wood. The bonding paste can only be processed by machine under certain conditions.

Specifications / technical data	Property	Test method	Value	Unit
	Density at 20 °C	DIN EN ISO 2811	approx. 0,72 - 0,76	g/ml
	Viscosity at 20 °C Brookfield RV/DV-II Spl 95 rpm 5	ISO 2555	300.000 - 400.000	mPas
	Styrene content		37 - 40	%
	Flash point	EN ISO 3679:2014 Verfahren B	32	°C

Curing	BÜFA method in accordance with DIN 16 945 6.2.2.1 (100 g bonding paste + 2 weight% Butanox M-60)	
	20 - 30 °C	30 - 40 min
	20 °C - Tmax	40 - 60 min
	Tmax	105 - 135 °C
	Gel time at 20 °C in a 100 g cup with 2 weight% Butanox M-60:	
		30 - 40 min

Attention!

The information given above refers exclusively to the use of the catalyst named and the quantity specified. The use of different products or differing quantities may yield different results.

BÜFA®-Bonding Paste 0072

UP Sandwich Adhesive

Prod. No. 7400072

Directions for use

If the bonding paste is mixed with the hardener by hand, the mixture should be poured into a second container after it has been thoroughly mixed to ensure homogenous distribution of the peroxide.

Storage/Handling

This product must be stored cool in closed containers, protected from sunlight. Shelf-life is at least 3 months in unopened, original containers stored up to a temperature of 20 °C. Gel and curing times may change with increasing duration of storage.

Note: The Information given above is based on our current state of knowledge and experience. In view of the many factors that may influence working conditions and the application of our products, the user is not relieved from carrying out his own tests and experiments. No legally binding warranty of certain properties or suitability for a particular purpose can be derived from this information. It is the responsibility of the receiver or user of our products to observe proprietary rights as well as existing laws and regulations. The latest version of the corresponding EU Safety Data Sheet must also be observed.

BÜFA Composite Systems GmbH & Co. KG
Hohe Looge 2-8
26180 Rastede
GERMANY
Phone +49 4402 975-0
Fax +49 4402 975-300
compositesystems@buefa.de
www.buefa.de
www.buefacompositesystems.com

A member of the BÜFA-Group